APPLICATION NO.	FILING DATE	FIRST NAMED INVENTOR	ATTORNEY DOCKET NO.	CONFIRMATION NO.
10/587,178	07/25/2006	Hideki Moriguchi	070456-0108	8002

20277   7590   01/20/2010
MCDERMOTT WILL & EMERY LLP
600 13TH STREET, N.W.
WASHINGTON, DC 20005-3096

EXAMINER
QUINLAN, RONALD A

ART UNIT	PAPER NUMBER
1794	

MAIL DATE	DELIVERY MODE
01/20/2010	PAPER

Please find below and/or attached an Office communication concerning this application or proceeding.

The time period for reply, if any, is set in the attached communication.

-- *The MAILING DATE of this communication appears on the cover sheet with the correspondence address* --

Period for Reply

A SHORTENED STATUTORY PERIOD FOR REPLY IS SET TO EXPIRE <u>3</u> MONTH(S) OR THIRTY (30) DAYS, WHICHEVER IS LONGER, FROM THE MAILING DATE OF THIS COMMUNICATION.
- Extensions of time may be available under the provisions of 37 CFR 1.136(a). In no event, however, may a reply be timely filed after SIX (6) MONTHS from the mailing date of this communication.
- If NO period for reply is specified above, the maximum statutory period will apply and will expire SIX (6) MONTHS from the mailing date of this communication.
- Failure to reply within the set or extended period for reply will, by statute, cause the application to become ABANDONED (35 U.S.C. § 133).
  Any reply received by the Office later than three months after the mailing date of this communication, even if timely filed, may reduce any earned patent term adjustment. See 37 CFR 1.704(b).

Status

1)☒ Responsive to communication(s) filed on *16 October 2009*.

2a)☒ This action is **FINAL**.   2b)☐ This action is non-final.

3)☐ Since this application is in condition for allowance except for formal matters, prosecution as to the merits is closed in accordance with the practice under *Ex parte Quayle*, 1935 C.D. 11, 453 O.G. 213.

Disposition of Claims

4)☒ Claim(s) *1-32* is/are pending in the application.

    4a) Of the above claim(s) _____ is/are withdrawn from consideration.

5)☐ Claim(s) _____ is/are allowed.

6)☒ Claim(s) *1-32* is/are rejected.

7)☐ Claim(s) _____ is/are objected to.

8)☐ Claim(s) _____ are subject to restriction and/or election requirement.

Application Papers

9)☐ The specification is objected to by the Examiner.

10)☒ The drawing(s) filed on *25 July 2006* is/are: a)☒ accepted or b)☐ objected to by the Examiner.

    Applicant may not request that any objection to the drawing(s) be held in abeyance. See 37 CFR 1.85(a).

    Replacement drawing sheet(s) including the correction is required if the drawing(s) is objected to. See 37 CFR 1.121(d).

11)☐ The oath or declaration is objected to by the Examiner. Note the attached Office Action or form PTO-152.

Priority under 35 U.S.C. § 119

12)☒ Acknowledgment is made of a claim for foreign priority under 35 U.S.C. § 119(a)-(d) or (f).

    a)☒ All b)☐ Some * c)☐ None of:

      1.☐ Certified copies of the priority documents have been received.

      2.☐ Certified copies of the priority documents have been received in Application No. _____.

      3.☒ Copies of the certified copies of the priority documents have been received in this National Stage application from the International Bureau (PCT Rule 17.2(a)).

    * See the attached detailed Office action for a list of the certified copies not received.

Attachment(s)

1)☒ Notice of References Cited (PTO-892)

2)☐ Notice of Draftsperson's Patent Drawing Review (PTO-948)

3)☐ Information Disclosure Statement(s) (PTO/SB/08)
    Paper No(s)/Mail Date _____.

4)☐ Interview Summary (PTO-413)
    Paper No(s)/Mail Date _____.

5)☐ Notice of Informal Patent Application

6)☐ Other: _____.

DETAILED ACTION

Claim Rejections - 35 USC § 103

1.   The following is a quotation of 35 U.S.C. 103(a) which forms the basis for all

obviousness rejections set forth in this Office action:

> (a) A patent may not be obtained though the invention is not identically disclosed or described as set
> forth in section 102 of this title, if the differences between the subject matter sought to be patented and
> the prior art are such that the subject matter as a whole would have been obvious at the time the
> invention was made to a person having ordinary skill in the art to which said subject matter pertains.
> Patentability shall not be negatived by the manner in which the invention was made.

2.   The factual inquiries set forth in *Graham* **v.** *John Deere Co.*, 383 U.S. 1, 148

USPQ 459 (1966), that are applied for establishing a background for determining

obviousness under 35 U.S.C. 103(a) are summarized as follows:

      1.   Determining the scope and contents of the prior art.
      2.   Ascertaining the differences between the prior art and the claims at issue.
      3.   Resolving the level of ordinary skill in the pertinent art.
      4.   Considering objective evidence present in the application indicating
          obviousness or nonobviousness.

3.   This application currently names joint inventors. In considering patentability of

the claims under 35 U.S.C. 103(a), the examiner presumes that the subject matter of

the various claims was commonly owned at the time any inventions covered therein

were made absent any evidence to the contrary. Applicant is advised of the obligation

under 37 CFR 1.56 to point out the inventor and invention dates of each claim that was

not commonly owned at the time a later invention was made in order for the examiner to

consider the applicability of 35 U.S.C. 103(c) and potential 35 U.S.C. 102(e), (f) or (g)

prior art under 35 U.S.C. 103(a).

4.   Claims 1-32 are rejected under 35 U.S.C. 103(a) as being unpatentable over JP

2001-353603 to Fukaya et al., hereinafter referred to as "Fukaya", in view of US

6,066,399 to Hirano et al., hereinafter referred to as "Hirano", in view of Sheeja et al.,

Tribological properties and adhesive strength of DLC coatings prepared under different

substrate bias voltages, Wear 249 (2001), pg. 433-439, hereinafter referred to as

"Sheeja" and as evidenced by Materials Science of Thin Films, Deposition and

Structure, Milton Ohring, 2nd Ed., 2004, hereinafter referred to as "Ohring".

5.   Regarding Claim 1, Fukaya (see Translation) teaches a surface coated cutting

tool (paragraph [0005]), comprising a base material (paragraph [0009]), a coated film

formed on said base material (paragraph [0009]), wherein said coated film serves as an

outermost layer on said base material and has compressive stress (paragraph [0009])

and is formed from a carbide, a nitride, an oxide, or a carbonitride selected from a group

comprising a Group IVa, Va, or VIa group elements of the periodic table, Al, B, and Ge

(paragraph [0009]). Fukaya teaches that the compressive stress is varied so as to have

strength distribution in a direction of thickness of said coated film (paragraphs [0012]

and [0013]), Figures 2-5). Fukaya teaches that having a maximum compressive stress

at the top surface of a coating is desirable for providing maximum toughness

(paragraphs [0007] and [0012] and also that decreasing the compressive stress from

the substrate to the surface of the film so that a minimum compressive stress is located

at the top surface of the coating is desirable for enhanced abrasion resistance

(paragraphs [0007] and [0013]). Fukaya further teaches said strength distribution is

characterized in that the compressive stress at the surface of said coated film

continuously decreases from said top surface of said coated film toward the bottom

surface of said coated film (Figure 2). Fukaya teaches the stepwise decrease of said

compressive stress from said top surface of said coated film toward the bottom surface of said coated film (Figure 3). Fukaya teaches the deposition of said layers through PVD techniques (paragraph [0029]).

6.   Fukaya does not teach that said strength distribution is characterized in that the compressive stress of said coated film continuously increases from a surface of said coated film toward a first intermediate point located between said surface of said coated film and a bottom surface of said coated film and the compressive stress attains a relative maximum point at said first intermediate point.

7.   Hirano teaches a hard carbon thin film as a protective coating on blades such as razor blades (col. 1, lines 12-21). Hirano teaches the hard carbon thin film as being formed on a base material (col. 2, lines 6-9) and a hardness and internal stress gradient through the carbon layer which serves as the outermost layer on the base material (col. 8, line 60 - col. 9, line 2). Hirano further teaches an example (col. 13, Example 4) in which the carbon thin film has a graded structure in which the sp^2/sp^3 ratio once decreases from a substrate/film interface to a minimum at an intermediate thickness of the thin film, and then increases therefrom toward a surface of the thin film (col. 13, lines 6-10 and Figure 5). Hirano teaches that the sp^2/sp^3 ratio is related to hardness and internal stress in the layers (col. 8, line 60 - col. 9, line 2). Hirano teaches that the graded film provides satisfactory hardness and excellent adhesion to the underlying substrate (col. 2, lines 10-19).

8.   Hirano further teaches that ion species, associated with formation of the thin film, in a plasma are varied in kinetic energy with film-forming time, so that the sp^2/sp^3 ratio in

the hard carbon thin film is varied in its thickness direction, and that in order to vary the

kinetic energies of those ion species, an acceleration voltage may be applied to them

(col. 3, lines 35-40). Hirano also teaches utilizing different acceleration voltages to

change the sp^2/sp^3 ratio at the surface of the film and throughout the thickness of the

film. Hirano teaches one example of starting the voltage at 2000 V during the beginning

of film growth, lowering the voltage to approximately 200 V at some intermediate point,

then returning the voltage to 2000 V (col. 13, Example 4, lines 19-33, Figure 13).

Hirano does not expressly explain that that high internal stress associated with the low

sp^2/sp^3 ratio is compressive stress.

9.   However, Sheeja discloses deposition of a high-hardness carbon film under

different substrate bias voltages. Sheeja shows that compressive stresses are formed

in hard carbon films from the formation of sp^3 carbon (low sp^2/sp^3 ratio) (page 433, 1.

Introduction and page 435, 3.3 Compressive stress of the film). Sheeja illustrates that a

compressive stress of 10 GPa is obtained when a substrate bias of 85 V is utilized and

the value is lower, approximately 1 GPa, when the substrate bias is higher, e.g., greater

than 3000 V (page 435, 3.3 Compressive stress of the film and Figure 3).

10.   One of ordinary skill in the art would expect the high internal stress as taught by

Hirano to inherently be compressive stress as evidenced by Sheeja. Hence the stress

distribution as taught by Hirano is characterized in that the compressive stress at the

surface of the coated film continuously increases from said surface toward an

intermediate point located between said surface and the substrate/film interface and

that the compressive stress attains a relative maximum point at the intermediate point.

11.   It is well known in the art that accelerating ions toward the substrate and
bombarding the surface induces compressive stress in a film, as it is considered atomic
peening action, as evidenced by Ohring (pages 184 and 748). Ohring also teaches that
it is well known in the art that substrate biasing may be used to induce compressive
stress in thin films and that by increasing the bias the internal stress of thin films may
reverse from tensile to compressive (page 748, section 12.5.3.3 and page 749, table
12-2). Because of this, the teachings of Hirano as evidenced by Sheeja may seem
counter intuitive. That compressive stress is induced in the film by "lowering" the
acceleration voltage. However, Sheeja teaches the reason for this apparent anomaly.
Sheeja explains that for carbon atoms, 85 V substrate bias is the optimum ion energy
from a balance between the incident carbon ions having sufficient energy to penetrate
the surface atomic layer, while minimizing the excess energy, which is dissipated during
the growth. In the case of deposition at high substrate bias voltages, the excess energy
may convert some of the sp^3 bonded to sp^2 bonded carbon atoms (page 435, 3.3
Compressive stress of the film). It is therefore considered well known in the art that for
carbon films, the norm holds true for the acceleration of ions up to 85 V, but then the
excess energy begins converting sp^3 bonded atoms to sp^2 bonded carbon atoms.

12.   Therefore it would have been obvious to one of ordinary skill in the art to modify
the compressive stress gradient of the coating as taught by Fukaya via the compressive
stress gradient as taught by Hirano as evidenced by Sheeja and Ohring. One of
ordinary skill in the art would have been motivated to do this so as to provide a wear
resistant and tough film as taught by Fukaya with satisfactory hardness and adhesion to

the underlying substrate as taught by Hirano. It should be noted that though Fukaya

discloses a film comprising a carbide, nitride, oxide or carbonitride and Hirano is

directed to a hard carbon film (or DLC), it is considered obvious for one of ordinary skill

in the art to compare the compressive stress profiles because both Fukaya and Hirano

discuss the importance of adhesion to the substrate, a satisfactory toughness and wear

resistance.

13.   It should also be noted that when the substrate bias or acceleration voltage is

mentioned without the use of a minus sign ("-"), there is not a different value attached.

The values are taken simply as absolutes and are used to indicate the potential

imparted to ions accelerating toward the surface to be coated.

14.   It should be noted for convenience that as interpreted by the teachings of Hirano

as evidenced by Sheeja, lower acceleration voltages for carbon films results in lower

sp^2/sp^3 ratios, which results in higher compressive stresses and that higher acceleration

voltage for carbon films results in higher sp^2/sp^3 ratios and lower compressive stresses.

15.   Regarding Claim 2, Fukaya teaches that the compressive stress is a minimum at

the surface of the film (Figures 4 and 5). Fukaya does not teach that the compressive

stress increases from the surface to an intermediate point and maintains a constant

value to the base side of the film.

16.   Hirano teaches an embodiment (col. 13, Example 4) in which the acceleration

voltage is at 200 V for the intermediate point (high compressive stress, as noted above)

of film growth and then increased to 2000 V (low compressive stress, as noted above)

and held there for the last minute of the film formation. Hirano teaches that the high

sp^2/sp^3 ratio formed at the surface results in a smooth surface (col. 9, lines 54-60).

Therefore one of ordinary skill in the art at the time of the invention would have

expected the compressive stress to be at a minimum at the surface of the carbon film

and increase continuously to the intermediate point of the film. Hirano also teaches the

ability to hold the acceleration voltage constant during the film growth resulting in a

continuous sp^2/sp^3 ratio (col. 11, Example 2, lines 54-57, Figure 10).

17.   Hirano does not teach a minimum compressive stress at the surface of the film,

obtaining a maximum compressive stress at an intermediate point in the film and then

maintaining a constant value from said first intermediate point to the bottom surface of

the coated film.

18.   Sheeja teaches that forming the carbon film with a high substrate bias, i.e., a

high sp^2/sp^3 ratio, results in a slightly lower coefficient of friction (page 432, Figure 7)

and that this may be desirable because the graphitic structure of the sp^2 carbon acts as

a solid lubricant on the surface of the film (page 438, 4. Discussion). Sheeja also

teaches that a low sp^2/sp^3 ratio film, formed with a lower substrate bias, results in a

harder film with a much lower wear rate (page 432, Figure 8). Sheeja further teaches

that one of ordinary skill in the art at the time of the invention would be motivated to

optimize the substrate bias during the formation of the hard film (page 438, 5.

Conclusion). Sheeja teaches forming the films at constant substrate biases (page 434,

2.1 Preparation of DLC film).

19.   Therefore it would have been obvious one of ordinary skill in the art at the time of

the invention to modify the compressive stress gradient of the film as taught by Fukaya

via the gradient as taught by Hirano. One of ordinary skill in the art would have been motivated to do this so as to provide a wear resistant and tough film as taught by Fukaya with satisfactory hardness and adhesion to the underlying substrate as taught by Hirano. It would have further been obvious to modify the sp^2/sp^3 ratio of Hirano via the acceleration voltages of Sheeja, as evidenced by Ohring so that the minimum compressive stress is present on the surface of the film, i.e., the sp^2/sp^3 ratio is high, and that the compressive stress remain constant from the intermediate point to the substrate. One of ordinary skill in the art at the time would have been motivated to do this in order to provide a low wear rate film as taught by Sheeja and to provide a smooth surface that can act as a solid lubricant as taught by Hirano and Fukaya.

20.   Regarding Claim 3, Sheeja further teaches that a substrate bias of 85 V results in a compressive stress of about 10 GPa (page 435, 3.3 Compressive stress of the film, Figure 3) and that a substrate bias of greater than 3000 V is approximately 1 GPa (page 435, 3.3 Compressive stress of the film, Figure 3). It is noted that it is well known in the art that the "-" (minus sign) represents an internal compressive stress and differentiates from an internal tensile stress, "+" (plus sign), as evidenced by applicant (specification, page 16, lines 16-20).

21.   Therefore it is expected by one of ordinary skill in the art that the compressive stress at any point in the film of Fukaya in view of Hirano in view of Sheeja, as evidenced by Ohring would be in a range from at least -10 GPa to at most 1 GPa, as shown in Sheeja (Figure 3).

22.   Regarding Claim 4, Fukaya in view of Hirano in view of Sheeja, as evidenced by Ohring teaches varying the acceleration voltage in a controlled fashion such that it starts at 2000 V, is varied in a constant manner to a minimum at 10 minutes and then increased back to the starting point of 2000 V (col. 13, Example 4, lines 19-25, Figure 13). The film forming time is shown to be 20 minutes (Figure 13). The intermediate point is interpreted as being located at a position distant from the top surface of the coated film by 50 % of the thickness of the film.

23.   Regarding Claim 5, Fukaya in view of Hirano in view of Sheeja as evidenced by Ohring teaches forming a compressive stress at the surface utilizing 2000 V and 200 V at the intermediate point. Sheeja shows that the compressive stress associated with 85 V is ~10 GPa and 3000 V is ~1 GPa.

24.   Fukaya in view of Hirano in view of Sheeja as evidenced by Ohring does not expressly teach the compressive stress at the surface of the film set to a value comparable to 25 to 95 % of the compressive stress at the intermediate point of the coated film.

25.   However, based on the curve indicated by the data of Sheeja (Figure 3), it would have been expected by one of ordinary skill in the art at the time of the invention, that the compressive stress of Hirano would be greater than 1 GPa at the ending acceleration voltage of 2000 V and less than 10 GPa at the intermediate acceleration voltage of 200 V. It also would be expected of one of ordinary skill in the art to modify the ratio of compressive stress at the surface and said intermediate point for the

purpose of increasing adhesion between layers/phases and preventing delamination of the film.

26.   Therefore it would have been obvious to one of ordinary skill in the art at the time of the invention to modify the compressive stress of the surface as taught by Fukaya in view of Hirano via the optimization as taught by Sheeja as evidenced by Ohring to vary the compressive stress value of the surface so that it was set to 25 to 95 % of the compressive stress at the intermediate point of the coated film. One of ordinary skill in the art at the time of the invention would have been motivated to do this to optimize the adhesion strength, wear resistance and hardness of the carbon film as taught by Sheeja, Hirano and Fukaya.

27.   Regarding Claim 6, Fukaya in view of Hirano in view of Sheeja as evidenced by Ohring does not expressly teach a compressive stress value for the surface of the film being set at a value comparable to 35 to 85 % of the compressive stress at the intermediate point of the coated film. However, it would be expected of one of ordinary skill in the art to modify the ratio of compressive stress at the surface and said intermediate point for the purpose of increasing adhesion between layers/phases and preventing delamination of the film.

28.   Therefore it would have been obvious to one of ordinary skill in the art at the time of the invention to modify the compressive stress of the surface as taught by Fukaya in view of Hirano via the optimization as taught by Sheeja to vary the compressive stress value of the surface so that it was set to 35 to 85 % of the compressive stress at the intermediate point of the coated film. One of ordinary skill in the art at the time of the

invention would have been motivated to do this to optimize the adhesion strength, wear resistance and hardness of the carbon film as taught by Sheeja, Hirano and Fukaya.

29.   Regarding Claim 7, Fukaya in view of Hirano in view of Sheeja as evidenced by Ohring teaches holding the acceleration voltage constant for the last minute of film growth after increasing the voltage from a maximum compressive stress at the intermediate point (Hirano, col. 13, Example 4, lines 19-25, Figure 13). This is interpreted as maintaining the compressive stress across a distance from the surface of the film and then increasing the compressive to a first intermediate point.

30.   Regarding Claim 8, Fukaya teaches continuously decreasing the compressive stress from the surface of the film to the base side of the film (Figure 2). Fukaya in view of Hirano as evidenced by Sheeja and Ohring teaches an embodiment in which the strength distribution is characterized in that the compressive stress continuously decreases from the first intermediate point toward the bottom surface of the coated film (Hirano, col. 13, Example 4, lines 19-33, Figure 13).

31.   Regarding Claim 9, Fukaya teaches a stress distribution between 0-10 GPa (paragraph [0009]). Fukaya also teaches control over the compressive stress and thickness of the film to prevent peeling (paragraphs [0010] and [0011]).

32.   Hirano teaches forming a hard film by starting with an acceleration voltage of 2000 V, then lowering the voltage to 200 V at the intermediate point and finally increasing the voltage back to 2000 V to finish the deposition.

33.   Sheeja shows that a substrate bias of 85 V results in a compressive stress of about 10 GPa (page 435, 3.3 Compressive stress of the film, Figure 3) and that a

substrate bias of greater than 3000 V is approximately 1 GPa (page 435, 3.3

Compressive stress of the film, Figure 3). It is noted that it is well known in the art that

the "-" (minus sign) represents an internal compressive stress and differentiates from an

internal tensile stress, "+" (plus sign), as evidenced by applicant (specification, page 16,

lines 16-20). Therefore, because Sheeja has identified the stress as an internal

compressive stress, the numerical values are interpreted absolute values.

34.   Therefore it is expected by one of ordinary skill in the art that the compressive

stress in the film of Hirano is in a range from at least -10 GPa to at most 1 GPa, as

evidenced by Sheeja (Figure 3) because the acceleration voltages are within the range

outlined by Sheeja.

35.   Therefore it would have been obvious to one of ordinary skill in the art to keep

the compressive stress of the film from 0-10 GPa as taught by Fukaya and Hirano. One

of ordinary skill in the art would be motivated to do this to prevent delamination of the

hard coating film.

36.   Regarding Claim 10, Fukaya teaches films of similar thicknesses (Table 3).

Fukaya in view of Hirano as evidenced by Sheeja and Ohring teaches varying the

acceleration voltage in a controlled fashion such that it starts at 2000 V, is varied in a

constant manner to a minimum at 10 minutes and then increased back to the starting

point of 2000 V (Hirano, col. 13, Example 4, lines 19-25, Figure 13). The film forming

time is shown to be 20 minutes (Hirano, Figure 13). The intermediate point is

interpreted as being located at a position distant from the top surface of the coated film

by 50 % of the thickness of the film.

37.   Regarding Claim 11, Fukaya teaches forming a film wherein the compressive

stress attains a minimum at the surface (paragraphs [0007] and [0012] and Figures 4

and 5).

38.   Fukaya in view of Hirano as evidenced by Sheeja and Ohring teaches an

acceleration voltage of 2000 V during the formation of the film's surface. Because the

acceleration voltage does not exceed 2000 V this is interpreted as the minimum of

compressive stress, as evidenced by Sheeja (Figure 3).

39.   Regarding Claim 12, Fukaya teaches a difference in the compressive stress by 1

GPa or approximately 10% (Figures 2-5). Fukaya in view of Hirano as evidenced by

Sheeja and Ohring teaches forming a compressive stress at the surface utilizing 2000 V

and 200 V at the intermediate point. Sheeja shows that the compressive stress

associated with 85 V is ~10 GPa and the compressive stress associate with 3000 V is

~1 GPa.

40.   Fukaya in view of Hirano as evidenced by Sheeja and Ohring does not expressly

teach the compressive stress at the surface of the film set to a value comparable to 25

to 95 % of the compressive stress at the intermediate point of the coated film.

41.   However, with the curve indicated by the data of Sheeja, it would have been

expected by one of ordinary skill in the art at the time of the invention that the

compressive stress of Hirano as evidenced by Sheeja and Ohring would be greater than

1 GPa at the ending acceleration voltage of 2000 V and less than 10 GPa at the

intermediate acceleration voltage of 200 V. Therefore it would have been expected of

one of ordinary skill in the art at the time of the invention to vary the compressive stress

of the surface as taught by Hirano as evidenced by Sheeja and Ohring so that it is set to

a value comparable to 25 to 95 % of the compressive stress at the intermediate point of

the coated film. One of ordinary skill in the art at the time of the invention would have

been expected to do this during optimization of the adhesion strength, wear resistance

and hardness of the film as demonstrated by Hirano (col. 2, lines 10-14).

42.   Regarding Claim 13, Fukaya in view of Hirano as evidenced by Sheeja and

Ohring does not expressly teach a compressive stress value for the surface of the film

being set at a value comparable to 35 to 85 % of the compressive stress at the

intermediate point of the coated film.

43.   It would have been obvious to one of ordinary skill in the art at the time of the

invention to vary the compressive stress of the surface as taught by Fukaya in view of

Hirano as evidenced by Sheeja so that it is set to a value comparable to 35 to 85 % of

the compressive stress at the intermediate point of the coated film. One of ordinary skill

in the art at the time of the invention would have been expected to do this during

optimization of the adhesion strength, wear resistance and hardness of the carbon film

as demonstrated by Hirano (col. 2, lines 10-14) and Fukaya (Table 3).

44.   Regarding Claim 14, Fukaya in view of Hirano as evidenced by Sheeja and

Ohring teaches holding the acceleration voltage constant for the last minute of film

growth after increasing the voltage from a minimum voltage (maximum compressive

stress) at the intermediate point (Hirano, col. 13, Example 4, lines 19-25, Figure 13).

This is interpreted as maintaining the compressive stress from the surface across a

distance from the surface toward the intermediate point and thereafter the compressive
stress continuously increases toward the intermediate point.

45.   Regarding Claim 15, Fukaya in view of Hirano as evidenced by Sheeja and
Ohring teaches holding the acceleration voltage constant for the first minute of film
growth and then decreasing the voltage continuously to the intermediate point. This is
interpreted (as evidenced by Sheeja and Ohring) as decreasing the compressive stress
from a maximum at the intermediate point toward a second intermediate point located
between the first intermediate point and the bottom surface of the film (Hirano, col. 13,
Example 4, lines 19-25, Figure 13).

46.   Regarding Claim 16, Fukaya teaches a compressive stress range of 0-10 GPa
for the film (paragraph [0009]). Hirano as evidenced by Sheeja and Ohring teaches
forming a hard carbon film by starting with an acceleration voltage of 2000 V, then
lowering the voltage to 200 V at the intermediate point and finally increasing the voltage
back to 2000 V to finish the deposition.

47.   Sheeja shows that a substrate bias of 85 V results in a compressive stress of
about 10 GPa (page 435, 3.3 Compressive stress of the film, Figure 3) and that a
substrate bias of greater than 3000 V is approximately 1 GPa (page 435, 3.3
Compressive stress of the film, Figure 3).

48.   Therefore it is expected by one of ordinary skill in the art that the compressive
stress in the film of Fukaya in view of Hirano is in a range from at least -10 GPa to at
most 1 GPa, as evidenced by Sheeja (Figure 3).

49.   Regarding Claim 17, Fukaya in view of Hirano as evidenced by Sheeja and
Ohring teaches varying the acceleration voltage in a controlled fashion such that it starts
at 2000 V, is varied in a constant manner to a minimum at 10 minutes and then
increased back to the starting point of 2000 V (Hirano, col. 13, Example 4, lines 19-25,
Figure 13). The film forming time is shown to be 20 minutes (Hirano, Figure 13). The
intermediate point is interpreted as being located at a position distant from the top
surface of the coated film by 50 % of the thickness of the film.

50.   Regarding Claim 18, Fukaya teaches varying the compressive stress in a
stepwise manner (Figures 3 and 5). Fukaya in view of Hirano as evidenced by Sheeja
and Ohring teaches that the second intermediate point is formed after 1 minute of film
growth and that the total film growth is 20 minutes (Hirano, Figure 13). Therefore the
second intermediate point is considered to be formed at 95 % of the thickness of the
coated film.

51.   Regarding Claim 19, Fukaya in view of Hirano as evidenced by Sheeja and
Ohring teaches an acceleration voltage of 2000 V during the formation of the film's
surface (Hirano, col. 13, Example 4, lines 19-25, Figure 13). Because the acceleration
voltage does not exceed 2000 V this is interpreted as the minimum of compressive
stress, as evidenced by Sheeja (Figure 3).

52.   Regarding Claim 20, Fukaya in view of Hirano as evidenced by Sheeja and
Ohring teaches forming a compressive stress at the surface utilizing 2000 V and 200 V
at the intermediate point. Sheeja shows that the compressive stress associated with 85
V is ~10 GPa and 3000 V is ~1 GPa.

53.   Fukaya in view of Hirano as evidenced by Sheeja and Ohring does not expressly teach the compressive stress at the surface of the film set to a value comparable to 25 to 95 % of the compressive stress at the intermediate point of the coated film.

54.   However, with the curve indicated by the data of Sheeja, it would have been expected by one of ordinary skill in the art at the time of the invention that the compressive stress of Hirano would be greater than 1 GPa at the ending acceleration voltage of 2000 V and less than 10 GPa at the intermediate acceleration voltage of 200 V. Therefore it would have been expected of one of ordinary skill in the art at the time of the invention to vary the compressive stress of the surface as taught by Hirano as evidenced by Sheeja and Ohring so that the compressive stress at the surface of the film is set to a value comparable to 25 to 95 % of the compressive stress at the first intermediate point of the coated film. One of ordinary skill in the art at the time of the invention would have been expected to do this during optimization of the adhesion strength, wear resistance and hardness of the carbon film as demonstrated by Hirano (col. 2, lines 10-14).

55.   Regarding Claim 21, Fukaya in view of Hirano as evidenced by Sheeja and Ohring does not expressly teach a compressive stress value for the surface of the film being set at a value comparable to 35 to 85 % of the compressive stress at the intermediate point of the coated film.

56.   It would have been expected of one of ordinary skill in the art at the time of the invention to vary the compressive stress of the surface as taught by Fukaya in view of Hirano as evidenced by Sheeja and Ohring so that the compressive stress at the

surface of the film is set to a value comparable to 35 to 85 % of the compressive stress

at the first intermediate point of the coated film. One of ordinary skill in the art at the

time of the invention would have been expected to do this during optimization of the

adhesion strength, wear resistance and hardness of the carbon film as demonstrated by

Hirano (col. 2, lines 10-14).

57.   Regarding Claim 22, Fukaya in view of Hirano as evidenced by Sheeja and

Ohring teaches holding the acceleration voltage of 2000 V constant during the final

minute of film formation and the formation of the film's surface (Hirano, col. 13, Example

4, Figure 13). Hirano teaches that the acceleration voltage was increased continuously

from the first intermediate point (after 10 minutes of growth) (col. 13, Example 4, Figure

13). This is interpreted as maintaining a compressive stress from the surface of the film

across a distance and then increasing the compressive stress continuously to the first

intermediate point.

58.   Regarding Claims 23-25, Fukaya in view of Hirano in view of Sheeja as

evidenced by Ohring teaches said strength distribution is characterized in that said

compressive stress continuously decreases from said first intermediate point toward a

second intermediate point located between said first intermediate point and said bottom

surface of said coated film and attains a relative minimum point at said second

intermediate point as noted above.

59.   Hirano teaches a specific embodiment of having a continuously decreasing

compressive stress from the top surface of the film to the bottom surface (substrate

side) of the film (col. 10, Example 1, Figure 8). Hirano also teaches a constant

compressive stress throughout the film to just above the bottom surface (substrate side) of the film (col. 11, Example 2, Figure 10). Hirano teaches a continuous increase in compressive stress from the top surface of the film to a first intermediate point in the film (maximum compressive stress) and then decreasing the compressive stress toward the bottom surface of the film (col. 13, Example 4, Figure 13). Finally, Hirano also teaches the stepwise increase of the compressive stress from the top surface of the film to an intermediate point in the film and then the stepwise decrease from the intermediate point to the bottom surface of the film (col. 13, Example 5, Figure 15). Hirano teaches a single growth time of 20 minutes.

60.   However, the steps of the increasing compressive stress, i.e., decreasing substrate bias, taught by Hirano may be interpreted as alternating and repeating manner of relative minimums and maximums in the film (formed at 4, 8, 12 and 16 minutes).

61.   Hirano in view of Sheeja as evidenced by Ohring does not expressly teach the formation of a maximum compressive stress at a first intermediate point, decreasing the compressive stress to a minimum at a second intermediate point, and then having a strength distribution with one or more relative maximum and minimums between the second intermediate point and the substrate.

62.   Sheeja teaches that one of ordinary skill in the art would be motivated to optimize the thickness and other parameters, such as substrate bias during the film formation (page 438, 5. Conclusion).

63.   Therefore it would have been obvious to one of ordinary skill in the art at the time
of the invention to modify the compressive stress gradient of Fukaya in view of Hirano
via the varying thickness of Sheeja and to modify the film of Fukaya in view of Hirano in
view of Sheeja to include multiple relative minimums and maximums in the film with vary
thicknesses. One of ordinary skill in the art at the time of the invention would have been
motivated to do this to optimize the adhesion strength, wear resistance and hardness of
the carbon film as taught by Sheeja, Hirano and Fukaya. It would be expected that
modifying the compressive stress of the film at varying intermediate points in the film
would result in increasing adhesion between layers/phases and preventing delamination
of the film while providing a low wear rate material as evidenced by Sheeja.

64.   Regarding Claim 26, Fukaya in view of Hirano in view of Sheeja as evidenced by
Ohring teaches forming a hard film by a compressive stress gradient. Hirano also
teaches forming multiple steps of stress in the film (col. 13, Example 5, Figure 15).

65.   Sheeja further teaches that a substrate bias of 85 V results in a compressive
stress of about 10 GPa (page 435, 3.3 Compressive stress of the film, Figure 3) and
that a substrate bias of greater than 3000 V is approximately 1 GPa (page 435, 3.3
Compressive stress of the film, Figure 3).

66.   Therefore it would have been obvious to one of ordinary skill in the art at the time
of the invention to modify the multiple relative minimums and maximums of compressive
stress of Fukaya in view of Hirano in view of Sheeja as evidenced by Ohring by the
optimization of compressive stress of Sheeja and that the compressive stress is in a
range of 10 GPa to 1 GPa. One of ordinary skill in the art at the time of the invention

would have been motivated to do this for the purpose of optimizing the adhesion

strength, wear resistance and hardness of the carbon film as taught by Sheeja, Hirano

and Fukaya.

67.   Regarding Claim 27, Fukaya in view of Hirano in view of Sheeja as evidenced by

Ohring further teaches the formation of stepwise increases in the compressive stress

from the surface of the hard film to the intermediate point of the film and then the

stepwise decrease of the compressive stress from the intermediate point to the bottom

surface of the film (Hirano, col. 13, Example 5, Figure 15). The first step point below the

surface of the film is for the final 4 minutes of growth (Hirano, col. 13, lines 55-61,

Figure 15). This is interpreted as being located at 20 % of the film's thickness.

68.   Fukaya in view of Hirano in view of Sheeja as evidenced by Ohring does not

expressly teach having a first intermediate point with a maximum compressive stress by

at least 0.1 % to at most 40 % of the thickness of the said coated film.

69.   However, because Hirano teaches the ability to obtain a relative maximum

located at 20 % of the film's thickness, it would have been obvious to one of ordinary

skill in the art at the time of the invention to have a first intermediate point of the multiple

relative maximums of compressive stress, as noted above, at 20 % of the film's

thickness distant from the top surface. One of ordinary skill in the art at the time of the

invention would have been motivated to do this for the purpose of optimizing the

adhesion strength, wear resistance and hardness of the carbon film as taught by

Sheeja. It would be expected that modifying the compressive stress of the film at

varying intermediate points in the film would result in increasing adhesion between

layers/phases and preventing delamination of the film while providing a low wear rate material as evidenced by Sheeja.

70.   Regarding Claim 28, Fukaya in view of Hirano in view of Sheeja as evidenced by Ohring teaches the formation of stepwise increases in the compressive stress from the surface of the hard film to the intermediate point of the film and then the stepwise decrease of the compressive stress from the intermediate point to the bottom surface of the film (Hirano, col. 13, Example 5, Figure 15). The first step point below the surface of the film is for the final 4 minutes of growth and the second step point below the surface of the film is at 12 minutes into the growth (Hirano, col. 13, lines 55-61, Figure 15). This is interpreted as being located at 40 % of the film's thickness distant from the top surface, as noted above.

71.   Therefore it would have been obvious to one of ordinary skill in the art at the time of the invention to have a first intermediate point of the multiple relative maximums of compressive stress as noted above at 20 % of the film's thickness distant from the top surface and said second intermediate point at 40 % of the film's thickness distant from the top surface. One of ordinary skill in the art at the time of the invention would have been motivated to do this for the purpose of optimizing the adhesion strength, wear resistance and hardness of the carbon film as taught by Sheeja, Hirano and Fukaya. It would be expected that modifying the compressive stress of the film at varying intermediate points in the film would result in increasing adhesion between layers/phases and preventing delamination of the film while providing a low wear rate material as evidenced by Sheeja.

72.   Regarding Claim 29, Fukaya teaches a minimum compressive stress at the surface of the film (Figures 2 and 3).

73.   Regarding Claim 30, Fukaya in view of Hirano in view of Sheeja as evidenced by Ohring as noted above teaches multiple relative minimums and maximums in the film with vary thicknesses.

74.   Hirano further teaches a maximum of compressive stress at an intermediate point (col. 13, Example 4, Figure 13) and a stepwise decrease from an intermediate maximum to the substrate (col. 13, Example 4, Figure 15). Hirano teaches that the step from the intermediate point with a maximum compressive stress to the next point in the stepwise decrease of compressive stress to the substrate is from 200 V to 1000 V.

75.   Sheeja teaches that a compressive stress of 10 GPa is introduced with a substrate bias of 85 V while a substrate bias of 3000 V introduced a 1 GPa compressive stress.

76.   Fukaya in view of Hirano in view of Sheeja as evidenced by Ohring does not expressly teach said compressive stress at said second intermediate point of said coated film is set to a value comparable to 10 to 80 % of the compressive stress at said first intermediate point of said coated film.

77.   However, a step corresponding to 3000 V to 85 V would be expected to produce a second intermediate point with approximately 10 % of the compressive stress of the first intermediate point. Therefore it would be expected by one of ordinary skill in the art that a step corresponding to 200 V and 1000 V would produce a second intermediate

point with at least 10 % of the compressive stress but not more than 80 % of the
compressive stress of the first intermediate point.

78.   Therefore it would have been obvious to one of ordinary skill in the art at the time
of the invention to modify the multiple steps of Fukaya in view of Hirano in view of
Sheeja as evidenced by Ohring via the optimization of Sheeja for the purpose of
creating multiple relative maximums and minimums in the carbon film. One of ordinary
skill in the art would have been motivated to do this for the purpose of optimizing the
adhesion strength, wear resistance and hardness of the film as taught by Sheeja. It
would be expected that modifying the compressive stress of the film at varying
intermediate points in the film would result in increasing adhesion between
layers/phases and preventing delamination of the film while providing a low wear rate
material as evidenced by Sheeja.

79.   Regarding Claim 31, Fukaya in view of Hirano in view of Sheeja as evidenced by
Ohring teaches varying the compressive stress in a stepwise manner throughout the
coated film. Sheeja teaches that one of ordinary skill in the art would be motivated to
optimize the film by varying the substrate bias and film thicknesses (page 438, 5.
Conclusion).

80.   Fukaya in view Hirano in view of Sheeja as evidenced by Ohring does not teach
said compressive stress at said second intermediate point of said coated film is set to a
value comparable to 20 to 60 % of the compressive stress at said fist intermediate point
of said coated film.

81.   However, it would have been obvious to one of ordinary skill in the art at the time

of the invention to modify compressive stress of said second intermediate point of

Fukaya in view of Hirano so that it was set to a value comparable to 20 to 60 % of the

compressive stress of said first intermediate point of the coated film for the purpose of

optimizing the adhesion strength, wear resistance and hardness of the film as taught by

Sheeja. It would be expected that modifying the compressive stress of the film at

varying intermediate points in the film would result in increasing adhesion between

layers/phases and preventing delamination of the film while providing a low wear rate

material as evidenced by Sheeja.

82.   Regarding Claim 32, Fukaya in view of Hirano in view of Sheeja as evidenced by

Ohring teaches holding the acceleration voltage constant for the last minute of film

growth after increasing the voltage from a minimum voltage (maximum compressive

stress) at the intermediate point (Hirano, col. 13, Example 4, lines 19-25, Figure 13).

This is interpreted as maintaining the compressive stress from the surface across a

distance from the surface toward the intermediate point and thereafter the compressive

stress continuously increases toward the intermediate point.

Response to Amendment

83.   The amendment of Claims 1, 3, 5, 6, 9, 12, 14, 16, 20, 22, 24-26 and 32 is

acknowledged.

84.   The objection to Claim 6 is withdrawn.

85.   The rejection of Claims 3, 9, 16 and 26 under 35 U.S.C. § 112, second

paragraph is withdrawn.

86.   Applicant's arguments with respect to Claims 1 and 8-22 rejected under 35
U.S.C. § 102(b) have been considered but are moot in view of the new ground(s) of
rejection.

87.   Applicant's arguments filed October 16, 2009 have been fully considered but they
are not persuasive.

88.   Regarding Claims 1-32, applicant argues that Hirano fails to disclose a film
formed from "a carbide, a nitride, an oxide, a carbonitride, an oxycarbide, an oxynitride,
or a carbide-nitride-oxide of at least one element selected from Iva-group elements, Va-
group elements, Via-group elements in the element periodic table, Al, B, Si and Ge, or a
solid solution thereof". However, as noted above, Fukaya teaches said film and as
noted above, Hirano as evidenced by (and/or in view of) Sheeja as evidenced by Ohring
remedy the deficiencies of Fukaya with the teachings of the varying compressive stress
gradients.

89.   Applicant has argued that Hirano is not relevant art because Hirano teaches the
coating of "shave blades" instead of a "cutting tool". Though Hirano teaches a carbon
film and Fukaya teaches a carbide, nitride or oxide film as noted above, the teaching of
the compressive stress profile are considered to be relevant because both Fukaya and
Hirano teach a need for wear resistance, toughness and adhesion to the substrate in
the coating film. Also, the limitations of the claim merely recite a "cutting tool" and do
not mention cutting ferrous material, and shaving blades are considered to be a cutting
tool as they do perform a cutting operation.

Conclusion

90.   Applicant's amendment necessitated the new ground(s) of rejection presented in this Office action. Accordingly, **THIS ACTION IS MADE FINAL**. See MPEP § 706.07(a). Applicant is reminded of the extension of time policy as set forth in 37 CFR 1.136(a).

91.   A shortened statutory period for reply to this final action is set to expire THREE MONTHS from the mailing date of this action. In the event a first reply is filed within TWO MONTHS of the mailing date of this final action and the advisory action is not mailed until after the end of the THREE-MONTH shortened statutory period, then the shortened statutory period will expire on the date the advisory action is mailed, and any extension fee pursuant to 37 CFR 1.136(a) will be calculated from the mailing date of the advisory action. In no event, however, will the statutory period for reply expire later than SIX MONTHS from the date of this final action.

92.   Any inquiry concerning this communication or earlier communications from the examiner should be directed to Ronald A. Quinlan whose telephone number is (571) 270-1149. The examiner can normally be reached on Monday to Thursday from 6:30am-4:30pm Eastern.

93.   If attempts to reach the examiner by telephone are unsuccessful, the examiner's supervisor, Jennifer McNeil can be reached on (571) 272-1540. The fax phone number for the organization where this application or proceeding is assigned is 571-273-8300.

94.   Information regarding the status of an application may be obtained from the Patent Application Information Retrieval (PAIR) system. Status information for

published applications may be obtained from either Private PAIR or Public PAIR.

Status information for unpublished applications is available through Private PAIR only.

For more information about the PAIR system, see http://pair-direct.uspto.gov. Should

you have questions on access to the Private PAIR system, contact the Electronic

Business Center (EBC) at 866-217-9197 (toll-free). If you would like assistance from a

USPTO Customer Service Representative or access to the automated information

system, call 800-786-9199 (IN USA OR CANADA) or 571-272-1000.

/R. A. Q./
Ronald A. Quinlan
Patent Examiner, Art Unit 1794
January 5, 2009

/Jennifer McNeil/
Supervisory Patent Examiner, Art Unit 1794